

AMENDMENT TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

1. (Original) A label comprising:
 - (A) a polymer facestock having an upper surface and a lower surface;
and
 - (B) an adhesive layer derived from at least one two-part, high solids curable adhesive overlying the lower surface of the polymer facestock.
2. (Original) The label of claim 1, wherein the adhesive cures without application of an external energy source.
3. (Original) The label of claim 1, wherein the two-part curable adhesive further comprises a tackifier or plasticizer, or a mixture thereof.
4. (Original) The label of claim 1, wherein the two-part curable adhesive has an initial tack sufficient to remain in a position when applied to a substrate.
5. (Original) The label of claim 1, wherein the two-part curable adhesive, when applied to the label, has a viscosity in the range from about 30,000 cps to about 120,000 cps.
6. (Original) The label of claim 1, wherein the coat weight of the adhesive layer is from about 5 to about 30 g/m².
7. (Currently amended) The label of claim 1, wherein the polymer facestock is comprises a polyester or poly- α -olefin or metallized polyolefin, or polylactic acid polymer.

8. (Currently amended) The label of claim 7, wherein the polymer facestock is comprises a biaxially oriented polypropylene or a biaxially oriented polyethylene terephthalate.

9. (Original) The label of claim 1, wherein the upper surface of the polymer facestock is corona treated or flame treated.

10. (Original) The label of claim 1, further comprising a barrier or tie coating layer between the polymer facestock and the two-part curable adhesive.

11. (Original) The label of claim 1, further comprising a print layer overlying the upper surface of the polymer facestock.

12. (Original) The label of claim 11, further comprising a transparent protective layer overlying the print layer.

13 . (Currently amended) The label of claim 44 12, wherein the protective layer comprises a polyamide, polyurethane, cellulosic polymer, silicone polymer, or any combination thereof.

14. (Original) The label of claim 11, further comprising a transparent abrasion, chemical, and/or ultraviolet resistant layer overlying the print layer.

15. (Original) The label of claim 11, further comprising an adhesion promoting layer between the upper surface of the polymer facestock and the print layer.

16. (Original) The label of claim 11, further comprising a layer of ink receptive composition between the upper surface of the polymer facestock layer and the print layer.

17. (Currently amended) The label of claim 1, wherein the adhesive comprises (a) an epoxy resin and a primary amine, a carboxylic acid or a carboxylic anhydride or a mixture of two or more thereof; (b) a cyclic anhydride and a primary amine; (c) an oxazoline and a primary amine, a carboxylic acid or a carboxylic anhydride or a mixture of two or more thereof; (d) a carbodiimide and primary amine or a carboxylic acid; or (e) an isocyanate and a primary amine, an alcohol or a carboxylic acid, or a mixture of two or more thereof; or (f) a mixture of two or more of (a)-(e).

18. (Currently amended) The label of claim 1, wherein the two-part curable adhesive comprises:

at least one epoxy resin which is a diglycidyl ether of a bisphenol, a diglycidyl ether of an aliphatic glycol, an epoxidized olefin, a polymer- or rubber-modified epoxy resin, or a mixture of two or more thereof; and

at least one an epoxy curing agent.

19. (Currently amended) The label of claim 18, wherein the epoxy curing agent is comprises a primary amine, diamine or polyamine; or a carboxylic acid, dicarboxylic acid, polycarboxylic acid, or an anhydride of such acid.

20. (Original) The label of claim 18, wherein the two-part curable adhesive further comprises a reactive diluent.

21. (Currently amended) The label of claim 1, wherein the two-part curable adhesive comprises ~~(b)~~ a cyclic anhydride and a primary amine.

22. (Currently amended) The label of claim 21, wherein the cyclic anhydride comprises a maleated polyolefin, terephthalic anhydride, naphthalic anhydride; pyromellitic dianhydride; 2,3,6,7-naphthalene tetracarboxylic dianhydride; 3,3',4,4'-diphenyl tetracarboxylic dianhydride; 1,2,5,6-naphthalene tetracarboxylic dianhydride; 2,2',3,3'-diphenyl tetracarboxylic dianhydride; 2,2-bis(3,4-dicarboxyphenyl) propane dianhydride; bis(3,4-dicarboxyphenyl) sulfone

dianhydride; 3,4,9,10-perylene tetracarboxylic dianhydride; bis(3,4-dicarboxyphenyl) ether dianhydride; naphthalene-1,2,4,5-tetracarboxylic dianhydride; naphthalene-1,4,5,8-tetracarboxylic dianhydride; 2,6-dichloronaphthalene-1,4,5,8-tetracarboxylic dianhydride; 2,7-dichloronaphthalene-1,4,5,8-tetracarboxylic dianhydride; 2,3,6,7-tetrachloronaphthalene-1,4,5,8-tetracarboxylic dianhydride; phenanthrene-1,8,9,10-tetracarboxylic dianhydride; 2,2-bis(2,3-dicarboxyphenyl) propane dianhydride; 1,1-bis(2,3-dicarboxyphenyl) ethane dianhydride; 1,1-bis(3,4-dicarboxyphenyl) ethane dianhydride; bis(2,3-dicarboxyphenyl) methane dianhydride; bis(3,4-dicarboxyphenyl) methane dianhydride; bis (3,4-dicarboxyphenyl) sulfone dianhydride; benzene-1,2,3,4-tetracarboxylic dianhydride; 3,4,3',4'-benzophenone tetracarboxylic dianhydride; 2,3,2',3'-benzophenone tetracarboxylic dianhydride; 2,3,3',4'-benzophenone tetracarboxylic dianhydride; pyrazine-2,3,5,6-tetracarboxylic dianhydride; thiophene-2,3,4,5-tetracarboxylic dianhydride, ~~similar dianhydrides, and~~ or mixtures of two or more of the foregoing.

23. (Currently amended) The label of claim 21, wherein the primary amine comprises methylene dianiline, meta-phenylene diamine, paraphenylene diamine, 4,4'-diaminodiphenyl sulfone, 3,3'-diaminodiphenyl sulfone, 4,4'-diaminodiphenyl oxide, 2,4-diaminotoluene, 3,3'-diaminodiphenyl methane, 1,3-diamino propane, 1,4-diamino butane, 1,6-diamino hexane, 1,8-diamino octane, 1,12-diamino dodecane, or ~~and~~ mixtures of two or more thereof.

24. (Currently amended) The label of claim 1, wherein the two-part curable adhesive comprises: e)

an oxazoline; and

a primary amine, a carboxylic acid or anhydride or a mixture of two or more thereof.

25. (Currently amended) The label of claim 24, wherein the oxazoline comprises 4,4', 5,5'-tetrahydro-2,2'-bisoxazole; a 2,2'-(alkanediyl) bis [4,5-dihydrooxazole], e.g., ~~2,2'-(1,4-butanediyl) bis [4,5-dihydrooxazole]; and 2,2'-(1-methyl-1,3-propanediyl) bis (4,5-dihydrooxazole);~~ a 2,2'-(arylene) bis [4,5-dihydrooxazole], e.g., ~~2,2'-(1,4-phenylene) bis [4,5-dihydrooxazole]; 2,2'-(1,5-naphthalenyl) bis [4,5-dihydrooxazole] and 2,2'-(1,8-anthracenyl) bis [4,5-dihydrooxazole];~~ and, a alkylene bis 2-(arylene) [4,5-dihydrooxazole], e.g., ~~methylene bis 2-(1,4-phenylene) [4,5-dihydrooxazole];~~ a 2,2',2''-(arylene) tris [4,5-dihydrooxazole], e.g., ~~2,2',2''-(1,3,5-phenylene) tris[4,5-dihydrooxazole];~~ oligomeric materials with pendent oxazoline groups such as poly [2-(alkenyl) 4,5-hydrooxazole], e.g., ~~poly [2-(2-propenyl) 4,5-dihydrooxazole];~~ and or mixtures of two or more thereof.


26. (Currently amended) The label of claim 24, wherein the carboxylic acid or cyclic anhydride comprises a maleated polyolefin, terephthalic anhydride, naphthalic anhydride; pyromellitic dianhydride; 2,3,6,7-naphthalene tetracarboxylic dianhydride; 3,3',4,4'-diphenyl tetracarboxylic dianhydride; 1,2,5,6-naphthalene tetracarboxylic dianhydride; 2,2',3,3'-diphenyl tetracarboxylic dianhydride; 2,2-bis(3,4-dicarboxyphenyl) propane dianhydride; bis(3,4-dicarboxyphenyl) sulfone dianhydride; 3,4,9,10-perylene tetracarboxylic dianhydride; bis(3,4-dicarboxyphenyl) ether dianhydride; naphthalene-1,2,4,5-tetracarboxylic dianhydride; naphthalene-1,4,5,8-tetracarboxylic dianhydride; 2,6-dichloronaphthalene-1,4,5,8-tetracarboxylic dianhydride; 2,7-dichloronaphthalene-1,4,5,8-tetracarboxylic dianhydride; 2,3,6,7-tetrachloronaphthalene-1,4,5,8-tetracarboxylic dianhydride; phenanthrene-1,8,9,10-tetracarboxylic dianhydride; 2,2-bis(2,3-dicarboxyphenyl) propane dianhydride; 1,1-bis(2,3-dicarboxyphenyl) ethane dianhydride; 1,1-bis(3,4-dicarboxyphenyl) ethane dianhydride; bis(2,3-dicarboxyphenyl) methane

dianhydride; bis(3,4-dicarboxyphenyl) methane dianhydride; bis (3,4-dicarboxyphenyl) sulfone dianhydride; benzene-1,2,3,4-tetracarboxylic dianhydride; 3,4,3',4'-benzophenone tetracarboxylic dianhydride; 2,3,2',3'-benzophenone tetracarboxylic dianhydride; 2,3,3',4'-benzophenone tetracarboxylic dianhydride; pyrazine-2,3,5,6-tetracarboxylic dianhydride; thiophene-2,3,4,5-tetracarboxylic dianhydride, the corresponding acids of any of the foregoing anhydrides, and or mixtures of two or more of the foregoing.

27. (Currently amended) The label of claim 24, wherein the primary amine comprises methylene dianiline, meta-phenylene diamine, paraphenylene diamine, 4,4'-diaminodiphenyl sulfone, 3,3'-diaminodiphenyl sulfone, 4,4'-diaminodiphenyl oxide, 2,4-diaminotoluene, 3,3'-diaminodiphenyl methane, 1,3-diamino propane, 1,4-diamino butane, 1,6-diamino hexane, 1,8-diamino octane, 1,12-diamino dodecane and or mixtures of two or more thereof.

28. (Currently amended) The label of claim 1, wherein the two-part curable adhesive comprises: ~~(d)~~
a carbodiimide; and
primary amine or a carboxylic acid, or a mixture of two or more thereof.

29. (Original) The label of claim 28, wherein the carbodiimide has the general structural formula:




or



wherein R and R' are independently a substituted or unsubstituted, branched or unbranched aliphatic or aromatic hydrocarbonyl group and x = 1 to about 100.

30. (Currently amended) The label of claim 28, wherein the primary amine comprises methylene dianiline, meta-phenylene diamine, paraphenylene diamine, 4,4'-diaminodiphenyl sulfone, 3,3'-diaminodiphenyl sulfone, 4,4'-diaminodiphenyl oxide, 2,4-diaminotoluene, 3,3'-diaminodiphenyl methane, 1,3-diaminopropane, 1,4-diaminobutane, 1,6-diaminohexane, 1,8-diaminooctane, 1,12-diaminododecane ~~and~~ or mixtures of two or more thereof.

31. (Currently amended) The label of claim 28, wherein the carboxylic acid is comprises a dicarboxylic acid having the general formula:



wherein R is a saturated or unsaturated aliphatic or an aromatic moiety having from 2 to about 30 carbon atoms.

32. (Currently amended) The label of claim 1, wherein the two-part curable adhesive comprises: (e)

an isocyanate; and

a primary amine, an alcohol or a carboxylic acid, or a mixture of two or more thereof.

33. (Original) The label of claim 32, wherein the isocyanate is a compound having the following formula:




wherein $n=2-4$, and Q denotes an aliphatic hydrocarbon group having 2 to about 18 carbon atoms, a cycloaliphatic hydrocarbon group having from 4 to about 15 carbon atoms, an aromatic hydrocarbon group having from 6 to about 18 carbon atoms, or an aryl-aliphatic hydrocarbon group having from about 8 to about 15 carbon atoms.

34. (Currently amended) The label of claim 33, wherein the amine is comprises an aliphatic, aromatic or aryl-aliphatic diamine or polyamine having a molecular weight of from about 60 to about 300.

35. (Currently amended) The label of claim 33, wherein the alcohol is comprises a saturated or unsaturated polyhydric alcohol having a molecular weight in the range from about 62 to about 400.

36. (Currently amended) The label of claim 33, wherein the carboxylic acid is comprises a dicarboxylic acid having the general formula:



wherein R is a saturated or unsaturated aliphatic or an aromatic moiety having from 2 to about 30 carbon atoms.

37. (Currently amended) A label comprising:

(A) a polymer facestock having an upper surface and a lower surface, wherein the polymer facestock is a biaxially oriented polyethylene terephthalate or polypropylene; and

(B) an adhesive layer derived from at least one high solids, curable adhesive composition comprising (a) an epoxy resin and a primary amine, a carboxylic acid or a carboxylic anhydride or a mixture of two or more thereof; (b) a cyclic anhydride and a primary amine; (c) an oxazoline and a primary amine, a carboxylic acid or a carboxylic anhydride or a mixture of two or more thereof; (d) a carbodiimide and primary amine or a carboxylic acid; or (e) an isocyanate and a primary amine, an alcohol or a carboxylic acid, or (f) a mixture of two or more thereof; or a mixture of two or more of (a)-(e).

38. (Original) A labeling process comprising the steps of (A) providing a substrate; (B) coating a two-part, high solids curable adhesive to one surface of a polymeric facestock; and (C) applying the adhesive coated surface of the polymeric facestock to the substrate.

39. (Original) The labeling process of claim 38, wherein the substrate is glass, plastic or metal.

40. (Currently amended) The labeling process of claim 38, wherein the adhesive comprises (a) an epoxy resin and a primary amine, a carboxylic acid or a carboxylic anhydride or a mixture of two or more thereof; (b) a cyclic anhydride and a primary amine; (c) an oxazoline and a primary amine, a carboxylic acid or a carboxylic anhydride or a mixture of two or more thereof; (d) a carbodiimide and primary amine or a carboxylic acid; or (e) an isocyanate and a primary

amine, an alcohol or a carboxylic acid, or (f) a mixture of two or more thereof; or a mixture of two or more of (a)-(e).

41. (Original) The labeling process of claim 38, wherein the polymer facestock is a biaxially oriented polyethylene terephthalate or polypropylene.

42. (New) The label of claim 25 wherein the oxazoline comprises 2,2'-(1,4-butanediyl) bis [4,5-dihydrooxazole], 2,2'-(1-methyl-1,3-propanediyl) bis (4,5-dihydrooxazole), 2,2'-(1,4-phenylene) bis [4,5-dihydrooxazole], 2,2'-(1,5-naphthalenyl) bis [4,5-dihydrooxazole], 2,2'-(1,8-anthracenyl) bis [4,5-dihydrooxazole], methylene bis 2-(1,4-phenylene) [4,5-dihydrooxazole], 2,2',2''-(1,3,5-phenylene) tris[4,5-dihydrooxazole], poly [2-(alkenyl) 4,5-hydrooxazole], or mixtures of two or more thereof.